



**UNITED CHEMICAL**

**United Chemical Company**

North Kaizhou Road, Puyang

Henan, China. 457000

[www.united-chem.cn](http://www.united-chem.cn)

Fax: 0086 393 4662499

Email: [technic@united-chem.cn](mailto:technic@united-chem.cn)

---

## Technical Data Sheet: UCA100L

---

**PRODUCT DESCRIPTION** UCA100L hydrocarbon resin is an aliphatic tackifier resins with an excellent compatibility with SIS, SIBS, and SBS block copolymers, EVA copolymers and nature rubber.

Excellent ageing stability

Improved Green tack

Outstanding Tack performance

Balance open and set time

Balance tackiness, adhesive strength and cohesive strength

### MAIN APPLICATION

Hot Melt Adhesives

Book Biding

Shoe adhesive

Pressure Sensitive Adhesive

Rubber Parts

### TYPICAL PROPERTIES

---

Appearance		Yellowish Granule
Color	Gardner in 50% toluene	5.0 max
Softening Point	°C	97-105
Ash Content	( wt.%)	0.05 max
Acid Value	(KOH mg/g)	0.30 max
Melt Viscosity	CPS(200 °C )	150-220
Flash Point	°C	275 min
Specific Gravity	20/20 °C	0.98
Heat Resistance	(200°C 3 h)Gardner	7.0 max

---

### PACKAGING

Packed in craft paper bags laminated with PE bags, 25kgs net weight and we also supply the packing according client request.

The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond United Chemical Company's control. The listed properties are illustrative only, and not product specifications. United Chemical Company disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of its products in combination with other material or in any process.