



**PUYANG UNITED CHEMICAL CO., LTD.**

RM.1008 CYBER BUSINESS BUILDING,  
ZHENXING ROAD, PUYANG, HENAN, CHINA.

TEL: 0086-393-4662488

[www.united-chem.cn](http://www.united-chem.cn)

**TECHNICAL DATA SHEET**

Rev.2202

**B-1200**

**B-1200** is 100% C5 Aliphatic hydrocarbon resin. The key feature of B-1200 is lower softening point, excellent initial adhesive and holding power.

The major usages of B-1200 are tackify a variety of adhesive polymers including natural rubber, synthetic polyisoprene, polyisobutylene, butyl rubber, AO,APAO, SIS and EVA.

**SPECIFICATIONS**

Softening Point (Ring & Ball, °C)	92 – 96	ASTM E 28
Initial Color (Yellow Index )	35 Max	ASTM D 6166
(Ga)	4.0 Max	ASTM D 6166
Wax Cloud Point (EVA/Resin/Wax=20/40/40)	120 Max	BDTM/Q-10
Melt Viscosity BRF, @200°C, cps	150 Max	ASTM D 3236

**TYPICAL PROPERTIES**

Softening Point (Ring & Ball, °C)	94	ASTM E 28
Initial Color (Yellow Index )	29	ASTM D 6166
(Ga)	3.5	ASTM D 6166
Wax Cloud Point (EVA/Resin/Wax=20/40/40)	70	BDTM/Q-10
Melt Viscosity BRF, @200°C, cps	80	ASTM D 3236
Molecular Weight (G.P.C, Mn)	1,000	
(G.P.C, Mw)	1,600	
D	1.6	

**PACKING**

**B-1200** is available both in 25Kg multi-ply paper bags and 500kg bags.

**STORAGE**

**B-1200** should be stored in cool ventilated dry place. Recommended temperature no exceeding 40°C.

The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond Puyang United Chemical's control. The listed -properties are illustrative only, and not product specifications. Puyang United Chemical disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of its products in combination with other material or in any process.